

## DESCRIPTION

|                             |        |                  |      |
|-----------------------------|--------|------------------|------|
| Total thickness             | EN 428 | mm               | 2.00 |
| Weight                      | EN 430 | g/m <sup>2</sup> | 2580 |
| Width of sheet              | EN 426 | cm               | 200  |
| Length of sheet             | EN 426 | lm               | 20   |
| Tile size                   | EN 427 | mm               |      |
| Number of tiles per package | -      | -                |      |






## CLASSIFICATION

|                              |             |       |                     |
|------------------------------|-------------|-------|---------------------|
| Norm / Product specification | -           | -     | EN 649              |
| European classification      | EN 685      | class | 34 - 43             |
| Fire rating                  | EN 13 501-1 | class | B <sub>fl</sub> -s1 |
| Static electrical propensity | EN 1815     | kV    | < 2                 |

## PERFORMANCE

|                                         |                 |                    |          |
|-----------------------------------------|-----------------|--------------------|----------|
| Wear resistance                         | EN 660.2        | mm <sup>3</sup>    | ≤ 2.0    |
| Wear Group                              | EN 649          | group              | T        |
| Type Binder content                     | ISO 10581       | type               | I        |
| Dimensional stability                   | EN 434          | %                  | ≤ 0.4    |
| Residual indentation                    | EN 433          | mm                 | ~ 0.03   |
| Castor chair test (type W)              | EN 425          | -                  | OK       |
| Thermal conductivity                    | EN 12 524       | W/(m.K)            | 0.25     |
| Colour fastness                         | EN 20 105 - B02 | degree             | ≥ 6      |
| Chemical products resistance            | EN 423          | class              | OK       |
| Anti-bacterial and fungicidal treatment | -               | -                  | OK       |
| Surface treatment                       | -               | -                  | Evercare |
| TVOC after 28 days                      | ISO 16000-6     | µg/ m <sup>3</sup> | < 10     |

## CE MARKING

|                                                                                    |          |   |                                                                                                                                                                                                                                                                   |
|------------------------------------------------------------------------------------|----------|---|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
|  | EN 14041 | - |    |
|                                                                                    |          | - |                                                                                                                                                                              |